

COOK SANDED STUCCO

The logo for Cook Brand, featuring the word "Cook" in a large, white, serif font with a registered trademark symbol, and the word "BRAND" in a smaller, white, sans-serif font below it. The logo is set against a dark blue background with a white swoosh element.

MANUFACTURER

A.W. Cook Cement Products
242 Amy Industrial Lane
Hoschton, GA 30548
Phone (706) 654-3677
Fax (706) 654-3662

DESCRIPTION

COOK SANDED STUCCO is a multi-purpose, multi-application product. The use of Portland cement, graded sands and air-entrained lime, makes an excellent alternative to job site mixing.

FEATURES

Addition of water only at job site Available in gray or white Use for scratch coat, brown coat or finish coat. Use as a parge coat over concrete block, precast concrete, or brick.

SURFACE PREPARATION

All concrete and masonry surfaces must be clean, dry and free from oil, grease, dirt, curing compounds, form release agents, mildew, loose paint or other foreign compounds that would deter the bond. Roughen smooth surfaces by sand blasting or grinding, this will also remove any foreign matter. Dilute COOK BONDING AGENT 1:1 with water, roll on to substrate and let dry clear before applying SANDED STUCCO.

MIXING

Add approx. 2 gallons of clean water to each 90 lb. bag to achieve a good workable consistency. The use of a mechanical mixer is recommended. Cooks Acrylic Liquid diluted 3:1 with water will enhance the mix through better bond, density, and flexibility..

APPLICATION

STUCCO – Follow the standard procedures of applying COOK SANDED STUCCO as outlined by ASTM C-926.

PARGE COAT -Apply approx. 1/8" to 1/4" thickness over concrete, brick or block. (Mix w/ Cook Acrylic Liquid diluted 2:1 with water) Cook bonding Agent diluted 1:1 w/ water should be applied prior to coating.

CURING

A light fog spray with clean water once or twice a day for 3 days is recommended to insure proper

curing.

COVERAGE

90 lbs. Will cover:
80-90 sq. ft @ 1/8"
40-45 sq. ft @ 1/4"
30-31 sq. ft @ 3/8"
20-23 sq. ft @ 1/2"

PRECAUTIONS

Contains Portland cement; avoid eye contact or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush with water for 15 minutes, Consult a physician immediately. Keep out of reach of children. Contains free silica – DO NOT breathe dust. May cause delayed lung injury. Follow OSHA safety and health standards for crystalline silica (quartz). See material safety data sheet for detailed information.

SPECIFICATIONS

Type I-II Cement ASTM C150 (white or gray)
Graded Sand ASTM C 897
A/E Lime ASTM C206 (Type S)
Sanded Stucco ASTM C 926

PACKAGING

COOK SANDED STUCCO 90 lb. bag

LIMITATIONS

Pigmented stucco may have color variations throughout a project. Varying amounts of powder & liquid, heat, wind, sun, humidity and finishing techniques all have effects on the coloring of cement. Because of these variables, A.W. COOK CEMENT PRODUCTS, INC. cannot be responsible for the exact color or any variations in the material.

NOTES

*** USE ONLY IN TEMPERATURES BETWEEN 40-100 DEGREES F. DO NOT MIX WITH ANY OTHER MATERIAL OTHER THAN WHAT IS STATED. ***