

# VALENCIA OLDE WORLD STUCCO

The logo for Cook Brand, featuring the word "Cook" in a large, white, serif font with a registered trademark symbol, and the word "BRAND" in a smaller, white, sans-serif font below it. The logo is set against a dark blue background with a white swoosh element.

## MANUFACTURER

A.W. Cook Cement Products  
242 Amy Industrial Lane  
Hoschton, GA 30548  
Phone (706) 654-3677  
Fax (706) 654-3662

## DESCRIPTION

VALENCIA OLDE WORLD STUCCO is a blend of Portland cement, pozzolan, lime, silica sand, polymers, water resistant additives and efflorescence inhibitors. A true cement plaster finish imparting iron oxide pigments that provide a natural, warm finish for interior or exterior applications.

## USES

As a finish coat for cement based substrates such as concrete block, scratch and brown coat, cement board, parge coats or existing brick.

## SURFACE PREPARATION

All surfaces must be sound and free from dirt, dust, paint, sealers, coatings, loose material, adhesives, curing compounds or any material that would inhibit material from coming in contact with concrete pores.

## APPLICATION

Dampen surfaces before application to a saturated, surface dry condition (SSD) and apply from 1/8" TO 1/4" thickness with various textures as desired. An alternate to pre-dampening is to prime the surface with COOK BRAND BONDING AGENT (diluted 1:1 with clean water) by brush or roller. Apply the diluted bonding agent and allow to dry clear, then apply finish coat.

## MIXING

Blend approx 1 1/4 gallons of cool clean water per 80 lb bag of VALENCIA OLDE WORLD STUCCO. Color packs should be added to the mixing water, followed by stucco powder and blended to a uniform, lump free consistency. Apply by spray method or by hand and finish to desired texture.

## AESTHETICS

VALENCIA OLDE WORLD STUCCO will provide a warm, textured finish with slight variations in color due to the natural pigments and finishing techniques. Care should be taken during application as many variables such as water content, wind, sun, humidity and temperature will give varying shades of color during installation and curing.

## FINISHES

Available in FINE GRADE and COARSE GRADE. Differences in each grade are achieved through the gradation of sand .

## LIMITATIONS

Do Not allow applied product to freeze for 48 hours after application. Do Not allow bonding agent to freeze. Air and substrate temperature should be between 40° F and 90° F. Color will vary with weather conditions at time of application.

## PACKAGING

FINE GRADE and COARSE GRADE are both available in 80 lb bags. Pigment pack weight will vary depending on color.

## PRECAUTIONS

Contains Portland cement; avoid eye contact or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush with 'water for 15 minutes, Consult a physician immediately. Keep out of reach of children. Contains free silica – DO NOT breathe dust. May cause delayed lung injury. Follow OSHA safety and health standards for crystalline silica (quartz). Keep out of reach of children. See material safety data sheet for detailed information.

## DISCLAIMER

Color variations can be expected due to differences in cement, aggregates and method of application. A jobsite mockup sample should be prepared prior to installation.